



DRIVING SURFACE PERFECTION™

RAPTOR

Test Report: Reference: - AB0818/4 – Page 1
Prepared August 2018
Authorized by A Blackburn

Brief: - Determination of drying time of EGC101 in Black in the manner of ASTM D1640.

Method:

Application: coating was applied using a Shutz gun at 50 psi. Application as a single medium coat.

Test conditions: 21°C with RH of 61%.

Dry Film Thickness: 9.2 Mil (233 microns)

7.2 Set-To-Touch Time: 30-minutes

7.3.1 Dust-Free Time (Cotton Fiber Test): 30-minutes

7.7 Dry-Through (Dry-To-Handle) Time: 60-minutes